



Epoxy Compound

DENACOL EX-861

Product feature

- Di-Functional Aliphatic type
- Water solubility
- Flexibility

Application

- Crosslinker for waterborne resin
- Hydrophilizing agent
- Flexibility-imparting agent

Chemical structure/name

Polyethylene Glycol Diglycidyl Ether

General Properties

Epoxy equivalent (g/eq.)	Viscosity (mPa·s)	Total chlorine content (%)	Color value (APHA)	Water solubility (%)
551	- (mp.45°C)	1.5	20	100

Each property and data introduced in this catalog, it is a representative value, NOT a guaranteed value. Also, please note that the specifications of the products are subject to change without notice.

Please read the Safety Data Sheet(SDS) before use.



More Information

Sales

NAGASE&CO.,LTI

Speciality 2nd section, Speciality Chemical department 5-1, Nihonbashi-Kobunacho, Chuo-ku, Tokyo 103-8355 Japan

TEL:+81-3-3665-3863 FAX:+81-3-3665-3970

lanufacture Nagase Chemtex Cornoration

